

Mycofabricated Silver Nanoparticles: An Overview of Biological Organisms Responsible for its Synthesis

**Nida Tabassum Khan and
Maham Jamil Khan**

Department of Biotechnology, Faculty of Life Sciences and Informatics, Balochistan University of Information Technology Engineering and Management Sciences, (BUIITEMS), Quetta, Pakistan

Corresponding author: Khan NT

✉ nidadtabassumkhan@yahoo.com

Department of Biotechnology, Faculty of Life Sciences and Informatics, Balochistan University of Information Technology Engineering and Management Sciences, (BUIITEMS), Quetta, Pakistan.

Tel: 03368164903

Citation: Khan NT, Khan MJ. Mycofabricated Silver Nanoparticles: An Overview of Biological Organisms Responsible for its Synthesis. *Biochem Mol Biol J.* 2017, 3:1.

Abstract

Silver nanoparticles are the most mentioned nanoparticles with increased production and commercialization along with widespread applications. Several studies revealed that the synthesis of nanoparticle of silver can be accomplished by employing numerous biological organisms such as plants, fungi, bacteria etc. to produce silver nanoparticles of enhanced properties.

Keywords: Fungi; Silver nanoparticles; Bacteria

Received: March 22, 2017; **Accepted:** April 18, 2017; **Published:** April 20, 2017

Introduction

Silver nanoparticles

Among different nanoparticles, Nanoparticles of silver is the most mentioned nanoparticle with increased production and commercialization along with widespread applications. A number of examples revealed that amalgamation of silver nanoparticles could be accomplished by using biological organisms. Extracellular synthesis of stable silver nano crystals has been documented in fungus *Aspergillus flavus* [1]. Similarly, endophytic fungi *Epicoccum nigrum* was found to synthesize Silver nanoparticles at different pH and temperature [2]. Similarly bacterias like *Bacillus* species and *Brevibacterium casei* are well known silver nanoparticle producers [3,4]. In addition spherical shaped silver nanoparticles of size 10-25 nm was reported to be synthesized by Curry leaf (*Murraya koenigii*) etc [5].

Synthetic approaches of silver nanoparticle synthesis

Presently there are quite a lot of methods employed in the fabrication of silver nanoparticles. But these approaches involve the applications of reducing agents like hydrazine [6], sodium borohydride [7], thiourea [8], thiophenol [9], mercaptoacetate [10] etc., which are hazardous and damaging to the environment. Such reducing agents make the synthesis process costly. Consequently biological synthesis of silver nanoparticle is now the most eco- friendly and cost effective process.

Biosynthesis of silver nanoparticle

Bio fabrication of silver nanoparticles could be accomplished

by employing different types of biological organisms such as bacteria, plants and fungi.

Bacteria in silver nanoparticle synthesis

Silver nanoparticles have been produced by different bacteria as enlisted in **Table 1**. Production of uniformly distributed Silver nanoparticles of size 50nm was reported in *Escherichia coli* [11,12]. Furthermore by varying the physiochemical factors such as pH, temperature, substrate concentration and incubation time, size of silver nanoparticle could be controlled [11]. On the other hand extremophilic *Ureibacillus thermosphaericus* was explored to have potential to produce silver nanoparticle at raised temperatures and increased silver ion concentrations. Using a concentration of 0.01 M AgNO₃ at 80°C temperature maximum yield of Silver nanoparticles could be achieved [13]. *Bacillus cereus* [14], *Bacillus thuringiensis* [15] and *Corynebacterium* strain SH09 [16] have also been reported to produce Silver nanoparticles. In another reported study, *Pediococcus pentosaceus*, *Lactococcus garvieae* and *Enterococcus faecium*, were used to produce Silver nanoparticles non-enzymatically through the interaction of organic compounds present on the surface of the bacterial cell

with silver ions. *Lactobacillus spp* depicts rapid synthesis of Silver nanoparticles for better silver nanoparticle recovery at high pH [17-31] etc.

Plants in silver nanoparticle synthesis

Names of well-known plants are enlisted in (Table 2) which is recognized as silver nanoparticle producers. Formation of silver nanoparticles at high temperature of 95°C was reported in *Cardiospermum helicacabum* leaf extracts [33]. Similarly rate of bioreduction is directly proportional to the broth concentration while studying the production of silver nanoparticle in Curry leaf (*Murraya koenigii*) extract [34]. Thus reaction kinetics and morphology of nanoparticles is affected by precursor solution (silver nitrate) and reductant (plant extract) concentration [35] as depicted during the formation of silver nanoparticle from an aqueous extract of *Pulicaria glutinosa*. Silver nanoparticles synthesis from clove extract [35] and *Aloe vera* plant extract [36] have also been reported. Myco-nanotechnology is the fabrication of metallic nanoparticles by employing fungi. This technology combines nanotechnology with mycology with extensive potential, mainly due to widespread occurrence and diversity of fungi [37-45]. Names of well-known fungal species have been enlisted in Table 3 which is currently recognized as silver nanoparticle producers [46-59].

Conclusion

Thus we can conclude that biological organisms such as Fungi, Bacteria, and plants could be employed as suitable nano-factories for the biological synthesis of nanoparticles of silver.

Table 2. List of plants synthesizing silver nanoparticle of various size.

S.no	Organism	Size(nm)
1	<i>Azadirachta indica</i>	50 [36]
2	<i>Carica papaya</i>	60–80 [37]
3	<i>Cinnamomum camphora leaf</i>	55–80 [38]
4	<i>Cinnamomum camphora Leaf</i>	5–40 [39]
5	<i>Coriandrum sativum leaf extract</i>	26 [40]
6	<i>Gliricidia sepium</i>	10–50 [41]
7	<i>Glycine max (soybean) leaf extract</i>	25–100 [42]
8	<i>Jatropha curcas</i>	10–20 [43]
9	<i>Phyllanthus amarus</i>	18–38 [44]

Table 1. List of bacteria synthesizing silver nanoparticle of various

S.no	Organism	Size (nm)
1	<i>Bacillus cereus</i>	4 and 5 [18]
2	<i>Bacillus licheniformis</i>	50 [19,20]
3	<i>Bacillus megaterium</i>	46.9 [21]
4	<i>Bacillus sp.</i>	5–15 [22]
5	<i>Bacillus subtilis</i>	5–60 [23]
6	<i>Brevibacterium casei</i>	50 [20]
7	<i>Corynebacterium sp.</i>	10–15 [16]
8	<i>Escherichia coli</i>	1–100 [24]
9	<i>Geobacter sulfurreducens</i>	200 [25]
10	<i>Klebsiella pneumonia (culture supernatant)</i>	50 [26]
11	<i>Lactic acid bacteria</i>	11.2 [27]
12	<i>Lactobacillus Strains</i>	500 [28]
13	<i>Morganella sp.</i>	20 [29]
14	<i>Proteus mirabilis</i>	10–20 [29]
15	<i>Pseudomonas stutzeri AG259</i>	200 [30]
16	<i>Staphylococcus aureus</i>	1–100 [31]

Table 3. List of fungi synthesizing silver nanoparticles.

S.no	Microorganism	Size (nm)
1	<i>Aspergillus clavatus</i>	10-25 [45]
2	<i>Aspergillus flavus</i>	1.61-8.92 [46]
3	<i>Aspergillus fumigatus</i>	5-25 [47]
4	<i>Aspergillus niger</i>	20 [48]
5	<i>Cladosporium cladosporioides</i>	10-100 [49]
6	<i>Fusarium acuminatum</i>	5-40 [50]
7	<i>Fusarium oxysporum</i>	5-50 [51]
8	<i>Fusarium semitectum</i>	10-60 [52]
9	<i>Fusarium solani</i>	5-35 [53]
10	<i>Penicillium brevicompactum WA 2315</i>	23-105 [54]
11	<i>Penicillium fellutanum</i>	1-100 [55]
12	<i>Phanerochaete chrysosporium</i>	100 [47]
13	<i>Trichoderma asperellum</i>	13-18 [56]
14	<i>Trichoderma viride</i>	5-40 [57]
15	<i>Verticillium sp.</i>	12-25 [58]
16	Yeast strain MKY3	2-5 nm [59]

References

- Rai M, Yadav A, Gade A (2009) Silver nanoparticles as a new generation of antimicrobials. *Biotechnology Advances* 27: 176–183.
- Qian Y, Yu H, He D, Yang H, Wang W, et al. (2013) Biosynthesis of silver nanoparticles by the endophytic fungus *Epicoccum nigrum* and their activity against pathogenic fungi. *Bioprocess and Biosystems Engineering* 36: 1613-1619.
- Kalimuthu K (2010) Biosynthesis of silver and gold nanoparticles using *Brevibacterium casei*. *Colloids and Surfaces B: Biointerfaces* 77: 257-262.
- Babu GMM, Gunasekaran P (2009) Production and structural characterization of crystalline silver nanoparticles from *Bacillus cereus* isolate. *Colloids Surf B Biointerfaces* 74: 191-195.
- Christensen L, Vivekanandhan S, Misra M, Mohanty AK (2011) Biosynthesis of silver nanoparticles using *Murraya koenigii* (curry leaf): An investigation on the effect of broth concentration in reduction mechanism and particle size. *Adv Mat Lett* 2: 429-434.
- Choudary BM, Madhi S, Chowdari NS, Kantam ML, Sreedhar B (2002) Layered double hydroxide supported nanopalladium catalyst for Heck-, Suzuki, Sonogashira, and Stille-type coupling reactions of chloroarenes. *J Am Chem Soc* 124: 14127–14136.
- Wang Y, Du MH, Xu JK, Yang P, Du YK (2008) Antifungal activity of silver nanoparticles. *Journal of Dispersion Science and Technology* 29: 891–894.
- Pattabi M, Uchil J (2000) Green synthesis of CdS nanoparticles and effect of capping agent concentration on crystallite size. *Solar Energy Mater Solar Cell* 63: 309–314.
- Ravindran TR, Arora AK, Balamurugan B, Mehta BR (2009) Resonance materials in physics biology and medicine. *Mater Res Innov* 13: 32-34.
- Liu SM, Liu FQ, Guo HQ, Zhang ZH, ZG (2000) Condensed matter physics and medicine. *Solid State Commun* 115: 615-618.
- Gurunathan S, Kalishwaralal K, Vaidyanathan R, Venkataraman D, Pandian SR, et al. (2009) Biosynthesis, purification and characterization of silver nanoparticles using *Escherichia coli*. *Colloids and Surfaces A: Biointerfaces* 74: 328-335.
- Sangiliyandi G, Kalishwaralal K, Vaidyanathan R, Venkataraman D, Pandian SR, et al. (2009) Biosynthesis, Purification and characterization of silver nanoparticles using *Escherichia coli*. *Colloids and Surfaces B: Biointerfaces* 74: 328-335.
- Juibari MM, Abbasalizadeh S, Jouzanib GS, Noruzic M (2011) Intensified biosynthesis of silver nanoparticles using a native extremophilic *Ureibacillus thermosphaericus* strain. *Materials Letters* 65: 1014–1017.
- Babu GMM, Gunasekaran P (2009) Production and structural characterization of crystalline silver nanoparticles from *Bacillus cereus* isolate. *Colloids Surf B Biointerfaces* 74: 191-195.
- Jain D, Kachhwaha S, Jain R, Srivastava G, Kothari SL (2010) Novel microbial route to synthesize silver nanoparticles using spore crystal mixture of *Bacillus thuringiensis*. *Indian J Exp Biol* 48: 1152-1156.
- Zhang H, Li Q, Lu Y, Sun D, Lin X, et al. (2005) Biosorption and bioreduction of diamine silver complex by *Corynebacterium*. *Journal of Chemical Technology and Biotechnology* 80: 285–290.
- Sintubin L, De Windt W, Dick J, Mast J, Van der Ha D, et al. (2009) Lactic acid bacteria as reducing and capping agent for the fast and efficient production of silver nanoparticles. *Appl Microbiol Biotechnol* 84: 741-749.
- Ganesh Babu MM, Gunasekaran P (2009) Production and structural characterization of crystalline silver nanoparticles from *Bacillus cereus* isolate. *Colloids Surf B* 74: 191–195.
- Kalimuthu K, Babu RS, Venkataraman D, Mohd B, Gurunathan S (2008) Biosynthesis of silver nanocrystals by *Bacillus licheniformis*. *Colloids Surf B* 65: 150–153.
- Kalishwaralal K, Deepak V, RamkumarPandian S, Nellaiah H, Sangiliyandi G (2008) Extracellular biosynthesis of silver nanoparticles by the culture supernatant of *Bacillus licheniformis*. *Mater Lett* 62: 4411–4413.
- Fu JK, Zhang WD, Liu YY, Lin ZY, Yao BX, et al. (1999) Characterization of adsorption and reduction of noble metal ions by bacteria. *Chin J Chem Univ* 20: 1452–1454.
- Pugazhenthiran N, Anandan S, Kathiravan G, Prakash NKU, Crawford S, et al. (2009) Microbial synthesis of silver nanoparticles by *Bacillus* sp. *J Nanopart Res* 11: 1811–1815.
- Saifuddin N, Wong CW, Nur yasumira AA (2009) Rapid biosynthesis of silver nanoparticles using culture supernatant of bacteria with microwave irradiation. *Eur J Chem* 6: 61–70.
- Gurunathan S, Kalishwaralal K, Vaidyanathan R, Venkataraman D, Pandian SRK, et al. (2009b) Biosynthesis, purification and characterization of silver nanoparticles using *Escherichia coli*. *Colloids Surf B* 74: 328–335.
- Law N, Ansari S, Livens FR, Renshaw JC, Lloyd JR. (2008) The formation of nano-scale elemental silver particles via enzymatic reduction by *Geobacter sulfurreducens*. *Appl Environ Microbiol* 74: 7090–7093.
- Ahmad RS, Sara M, Hamid RS, Hossein J, Ashraf-Asadat N (2007) Rapid synthesis of silver nanoparticles using culture supernatants of Enterobacteria: A novel biological approach. *Process Biochem* 42: 919–923.
- Nair B, Pradeep T (2002) Coalescence of nanoclusters and formation of submicron crystallites assisted by *Lactobacillus* strains. *Cryst. Growth Des* 2: 293-298.
- Parikh RY, Singh S, Prasad BL, Patole MS, Sastry M, et al. (2008) Extracellular synthesis of crystalline silver nanoparticles and molecular evidence of silver resistance from *Morganella*. sp. towards understanding biochemical synthesis mechanism. *Chem Biochem* 9: 1415–1422.
- Tanja K, Ralph J, Eva O, Claes- Georan G (1999) Silver-based crystalline nanoparticles, microbially fabricated. *Proc Natl Acad Sci* 96: 13611–13614.
- Nanda A, Saravanan M (2009) Biosynthesis of silver nanoparticles from *Staphylococcus aureus* and its antimicrobial activity against MRSA and MRSE. *Nanomedicine* 5: 452–456.
- Mitra B, Vishnudas D, Sant SB, Annamalai A (2012) Green-synthesis and characterization of silver nanoparticles by aqueous leaf extracts of *Cardiospermum helicacabum* leaves. *Drug Invention Today* 4: 340-344.
- Christensen L, Vivekanandhan S, Misra M, Mohanty AK (2011) Biosynthesis of silver nanoparticles using *Murraya koenigii* (curry leaf): An investigation on the effect of broth concentration in reduction mechanism and particle size. *Adv Mat Lett* 2: 429-434.
- Khan M, Khan M, Adil SF, Tahir MN, Tremel W, et al.(2013) Green synthesis of silver nanoparticles mediated by *Pulicaria glutinosa* extract. *Int J Nanomedicine* 8: 1507-1516.
- Singh AK, Talat M, Singh DP, Srivastava ON (2010) Biosynthesis of gold and silver nanoparticles by natural precursor clove and their functionalization with amine group. *J Nanopart Res* 12: 1667–1675.

- 35 Chandran SP, Chaudhary M, Pasricha R, Ahmad A, Sastry M (2006) Synthesis of gold nanotriangles and silver nanoparticles using *Aloe vera* plant extract. *Biotechnol Prog* 22: 577-583.
- 36 Shankar SS, Rai A, Ahmad A, Sastry M (2004) Rapid synthesis of Au, Ag and bimetallic Au core-Ag shell nanoparticles using neem (*Azadirachta indica*) leaf broth. *J. Colloid Interface Sci* 275: 496-502.
- 37 Mude N, Ingle A, Gade A, Rai M (2009) Synthesis of silver nanoparticles using callus extract of *Carica papaya* – A first report. *J Plant Biochem Biotechnol* 18: 83-86.
- 38 Huang J, Li Q, Sun D, Lu Y, Su Y (2007) Biosynthesis of silver and gold nanoparticles by novel sundried *Cinnamomum camphora* leaf. *Nanotechnology* 18: 105104.1-105104.11.
- 39 Huang J, Lin L, Li Q, Sun D, Wang Y, et al. (2008) Continuous-flow biosynthesis of silver nanoparticles by lixivium of Sundried *Cinnamomum camphora* leaf in tubular microreactors. *Ind Eng Chem Res* 47: 6081-6090.
- 40 Sathyavathi R, Krishna MB, Rao SV, Saritha R, Rao DN (2010) Biosynthesis of silver nanoparticles using *Coriandrum sativum* leaf extract and their application in nonlinear optics. *Adv Sci Lett* 3: 138-143.
- 41 Raut R, Jaya SL, Niranjana DK, Vijay BM, Kashid S (2009) Photosynthesis of silver nanoparticle using *Gliricidia sepium* (Jacq.). *Curr Nanosci* 5: 117-122.
- 42 Vivekanandhan S, Misra M, Mohanty AK (2009) Biological synthesis of silver nanoparticles using Glycine max (soybean) leaf extract: An investigation on different soybean varieties. *J Nanosci Nanotechnol* 9: 6828-6833.
- 43 Bar H, Bhui DK, Gobinda PS, Priyanka S, Santanu P, et al. (2009) Green synthesis of silver nanoparticles using seed extract of *Jatropha curcas*. *Colloids Surf A Physico Chem Eng Asp* 348: 212-216.
- 44 Kasthuri J, Kathiravan K, Rajendiran N (2009) Phyllanthin-assisted biosynthesis of silver and gold nanoparticles: A novel biological approach. *J Nanopart Res* 11: 1075-1085.
- 45 Verma VC, Kharwar RN, Gange AC (2010) Biosynthesis of antimicrobial silver nanoparticles by the endophytic fungus *Aspergillus clavatus*. *Nanomedicine* 5: 33-40.
- 46 Vigneshwaran N, Kathe A (2007) Silver-protein (core-shell) nanoparticle production using spent mushroom substrate. *Langmuir* 23: 7113-7117.
- 47 Bhainsa KC, D Souza SF (2006) Extracellular biosynthesis of silver nanoparticles using the fungus *Aspergillus fumigatus*. *Colloids and Surfaces B: Biointerfaces* 47: 160-164.
- 48 Gade A, Bonde PP, Ingle AP, Marcato P, Duran N, et al. (2008) Exploitation of *Aspergillus niger* for synthesis of silver nanoparticles. *J Biobased Mater Bio*. 2: 1-5.
- 49 Balaji DS, Basavaraja S, Deshpande R, Bedre D, Prabhakar BK, et al. (2009) Extracellular biosynthesis of functionalized silver nanoparticles by strains of *Cladosporium cladosporioides* fungus. *Colloids and Surfaces B: Biointerfaces* 68: 88-92.
- 50 Ingle A, Gade A, Pierrat S, Soñnichen C, Rai M (2008) Mycosynthesis of silver nanoparticles using the fungus *F. acuminatum* and its activity against some human pathogenic bacteria. *Curr Nanosci* 4: 141-144.
- 51 Kumar SA, Abyaneh MK, Gosavi SW, Kulkarni SK, Pasricha R, et al. (2007b) Nitrate reductase-mediated synthesis of silver nanoparticles from AgNO₃. *Biotechnology Letters* 29: 439-445.
- 52 Basavaraja S, Balaji SD, Lagashetty A, Rajasab AH, Venkataraman A (2007) Extracellular biosynthesis of silver nanoparticles using the fungus *Fusarium semitectum*. *Material Research Bulletin* 43: 1164-1170.
- 53 El-Rafie MH, Mohamed AA, Shaheen THI, Hebeish A (2010) Anti-microbial effect of silver nanoparticles produced by fungal process on cotton fabrics. *Carbohydr Polym* 80: 779-782.
- 54 Shaligram NS, Bule M, Bhambure R, Singhal RS, Singh SK, et al. (2009) Biosynthesis of silver nanoparticles using aqueous extract from the compactin producing fungal strain. *Proc Biochem* 44: 939-943.
- 55 Kathiresan K, Manivannan S, Nabeel AM, Dhivya B (2009) Studies on silver nanoparticles synthesized by a marine fungus *Penicillium fellutanum* isolated from coastal mangrove sediment. *Colloids Surf B* 71: 133-137.
- 56 Mukherjee P, Roy M, Mandal BP, Dey GK, Mukherjee PK, et al. (2008) Green synthesis of highly stabilized nanocrystalline silver particles by a non-pathogenic and agriculturally important fungus *asperellum*. *Nanotechnology* 19: 103-110.
- 57 Fayaz AM, Balaji K, Girilal M, Yadav R, Kalaichelvan PT, et al. (2010) Biogenic synthesis of silver nanoparticles and their synergistic effect with antibiotics: A study against gram-positive and gram-negative bacteria. *Nanomed. Nanotechnol. Biol. Med* 6: 103-109.
- 58 Mukherjee P, Ahmad A, Mandal D, Senapati S, Sainkar SR, et al. (2001) Fungus-mediated synthesis of silver nanoparticles and their immobilization in the mycelial matrix: a novel biological approach to nanoparticle synthesis. *Nano* 1: 515-519.
- 59 Kowshik M, Ashtaputre S, Kharrazi S, Vogel W, Urban J, et al. (2003) Extracellular synthesis of silver nanoparticles by a silver-tolerant yeast strain MKY3. *Nanotechnology* 14: 95-100.